

PVD Coated Grade for High Precision and Small Parts Machining

MS9025





PVD Coated Grade for High Precision and Small Parts Machining

MS9025


Effective reduction of notch wear with a balance of wear and fracture resistance.


Features

Improved Cemented Carbide


Thermal conductivity has been improved by optimising the grain size and therefore reducing the boundary contact between the WC particles. This optimisation reduces the temperature of the cutting edge during machining.


MS9025





Conventional






Reducing the cutting edge temperature by improved thermal conductivity.

Higher cutting edge temperatures due to more particle boundary contact.

Smooth Surface of The Coating

The even surface of the coating has been achieved by first making the the carbide substrate smooth then by promoting straight growth of the coating crystals. This leads to excellent welding resistance.


MS9025





Straight crystal growth. Smooth carbide surface. Excellent welding resistance.

Conventional




Rough Cemented Carbide

Random crystal growth direction. Performance is variable due to defects and voids in the surface.

New Technology - Controlled Vibration of the Cutting Tool

Using new machine technology to deliberately vibrate the tool in relation to the cutting direction is an effective way of breaking chips.

This reduces production costs by reducing chip entanglement.




Challenges of controlled vibration machining:

Compared to standard machining there is a greater chance of edge chipping due to the extra stress on the cutting edge and also because of the impact of work hardening.

Benefits of using MS9025 for Controlled Vibration Machining


- 1. Excellent fracture resistance due to the inherent toughness of the base material.
- 2. Effectively suppresses boundary wear damage during machining of difficult-to-cut materials. This is achieved by the optimised cemented carbide grain size that reduces thermal conductivity and heating of the cutting edge.

After 500 passes at 15m per pass




High Al-rich(Al,Ti)N Single Layer Coating Technology





High Al and Conventional Coating Comparison

The high Al-rich (Al,Ti)N single layer coating provides stabilization of the high hardness phase and succeeds in dramatically improving wear, creater and welding resistance.



Extremely High Quality Cutting Edge

Technology that provides superior dimensional stability and reduces burrs.

MS9025


Rz=0.14 µm



Rz=0.61 µm

Cutting Performance

Stainless Steel SUS440C, Wear Resistance Comparison



<Cutting Conditions>


Workpiece Material : JIS SUS440C Inserts : DCGT11T302 Machining Methods : External

Continuous Cutting
Cutting Speed : vc = 100 m/min
Feed per Rev. : f = 0.08 mm/rev
Depth of Cut : ap = 1.0 mm
Cutting Mode : Wet Cutting (Oil)

Taken after machining 500 Parts







MS9025


Conventional C : Flaking

Conventional D : Base material exposure

Stainless Steel SUS304, Cutting Edge Comparison


After machining 500 parts

MS9025



VB=0.03mm

Conventional



Notch Wear

VB=0.07 mm

<Cutting Conditions>

Cutting Mode

Workpiece Material : JIS SUS304 Inserts : DCGT11T302

Machining Methods : External

Continuous Cutting
Cutting Speed : vc = 57 m/min
Feed per Rev. : f = 0.03 mm/rev
Depth of Cut : Rough ap = 0.05 mm


Finish ap = 0.02 mm : Wet Cutting (Oil)

MS9025



7° Positive Inserts (With Hole)

G Class



Finish

Light

Medium

				U.		(mm)
Order Number	Cutting Area	MS9025	IC	s	RE	D1
CCGT060201M-FS-P	F	•	6.35	2.38	0.1	2.8
CCGT060202M-FS-P	F	•	6.35	2.38	0.2	2.8
CCGT09T301M-FS-P	F	•	9.525	3.97	0.1	4.4
CCGT09T302M-FS-P	F	•	9.525	3.97	0.2	4.4
CCGT09T304M-FS-P	F	•	9.525	3.97	0.4	4.4
CCGT060201M-LS-P	L	•	6.35	2.38	0.1	2.8
CCGT060202M-LS-P	L	•	6.35	2.38	0.2	2.8
CCGT09T301M-LS-P	L	•	9.525	3.97	0.1	4.4
CCGT09T302M-LS-P	L	•	9.525	3.97	0.2	4.4
CCGT09T304M-LS-P	L	•	9.525	3.97	0.4	4.4
CCGT060201MR-SN	М	•	6.35	2.38	0.1	2.8
CCGT060202MR-SN	М	•	6.35	2.38	0.2	2.8
CCGT09T301MR-SN	М	•	9.525	3.97	0.1	4.4
CCGT09T302MR-SN	М	•	9.525	3.97	0.2	4.4
CCGT09T304MR-SN	М	•	9.525	3.97	0.4	4.4
DCGT070201M-FS-P	F	•	6.35	2.38	0.1	2.8
DCGT070202M-FS-P	F	•	6.35	2.38	0.2	2.8
DCGT070204M-FS-P	F	•	6.35	2.38	0.4	2.8
DCGT11T301M-FS-P	F	•	9.525	3.97	0.1	4.4
DCGT11T302M-FS-P	F	•	9.525	3.97	0.2	4.4
DCGT11T304M-FS-P	F	•	9.525	3.97	0.4	4.4
DCGT11T301MR-SRF	F	•	9.525	3.97	0.1	4.4
DCGT11T302MR-SRF	F	•	9.525	3.97	0.2	4.4
DCGT11T304MR-SRF	F	•	9.525	3.97	0.4	4.4
DCGT070201M-LS-P	L	•	6.35	2.38	0.1	2.8
DCGT070202M-LS-P	L	•	6.35	2.38	0.2	2.8
DCGT070204M-LS-P	L	•	6.35	2.38	0.4	2.8
DCGT11T301M-LS-P	L	•	9.525	3.97	0.1	4.4
DCGT11T302M-LS-P	L	•	9.525	3.97	0.2	4.4
DCGT11T304M-LS-P	L	•	9.525	3.97	0.4	4.4
DCGT070201MR-SN	М	•	6.35	2.38	0.1	2.8
DCGT070202MR-SN	М	•	6.35	2.38	0.2	2.8
DCGT070204MR-SN	М	•	6.35	2.38	0.4	2.8
DCGT11T301MR-SN	М	•	9.525	3.97	0.1	4.4
DCGT11T302MR-SN	М	•	9.525	3.97	0.2	4.4
DCGT11T304MR-SN	М	•	9.525	3.97	0.4	4.4


ı	Recommended Cutting Conditions (mm)									
		Workpiece Material	Properties	Cutting Area		Chip Breaker	Grade	Cutting Speed vc (m/min)	Feed per Rev. f (mm/rev)	Depth of Cut ap
	M			•	F	FS-P	MS9025	100(50—180)	0.04-0.12	0.2-1.4
	Electromagnetic Stainless Steels	Hardness	<u>e</u>	F	R-SRF	MS9025	100(50—180)	0.05-0.12	0.1-0.5	
		(SUS440C, SUS420J2 etc.)	230HBW	<u>e</u>	L	LS-P	MS9025	100(50—180)	0.04-0.15	0.3-3.0
				<u>G</u>	М	R-SN	MS9025	100(50—180)	0.01-0.10	0.1-5.0
	S	Heat Resistant Alloys (SUH etc.)		•	F	FS-P	MS9025	80(40—140)	0.04-0.12	0.2-1.4
				•	F	R-SRF	MS9025	80(40—140)	0.05-0.12	0.1-0.5
			_	¢	L	LS-P	MS9025	80(40—140)	0.04-0.15	0.3-3.0
				c	М	R-SN	MS9025	80(40—140)	0.01-0.10	0.1-5.0

Cutting Conditions (Guide):

●: Stable Cutting ●: General Cutting \$: Unstable Cutting

Application Examples

	Insert	DCGT11T302M-LS-P	DCGT070201M-FS-P			
	Workpiece	JIS SUS420J2 Stainless Steel	JIS SUS440C Electromagnetic Stainless Steel			
	Component	Solenoid Parts	Brake Parts			
	Application	External Continuous Turning	External Continuous Turning			
lifons	Cutting Speed vc (m/min)	117	38			
Cutting Conditions	Feed per Rev. f (mm/rev)	0.1	0.05			
all display	Depth of Cut ap (mm) Cutting Mode O.2 Wet Cutting (Oil)		0.2			
			Wet Cutting (Oil)			
	Results	Number of Workpieces 5000 1000 1500 MS9025 Conventional Improved wear resistance and tool life increased by a factor of 1.7.	Number of Workpieces 1000 2000 3000 MS9025 Conventional Improved welding resistance and double tool life when compared to a conventional tool.			



The application examples are from customers workpieces and can therefore differ from the recommended cutting conditions.

For Your Safety

Don't handle inserts and chips without gloves. Please machine within the recommended application range and exchange expired tools with new ones in advance of breakage. Please use safety covers and wear safety glasses. When using compounded cutting oils, please take fire precautions. When attaching inserts or spare parts, please use only the correct wrench or driver. When using rotating tools, please make a trial run to check run-out, vibration and abnormal sounds etc.

AMITSUBISHI MATERIALS CORPORATION

MITSUBISHI MATERIALS CORPORATION

Overseas Sales Dept, Asian Region

KFC bldg., 8F, 1-6-1 Yokoami, Sumida-ku, Tokyo 130-0015, Japan TEL +81-3-5819-8771 FAX +81-3-5819-8774

Overseas Sales Dept, European & American Region

KFC bldg., 8F, 1-6-1 Yokoami, Sumida-ku, Tokyo 130-0015, Japan TEL +81-3-5819-8772 FAX +81-3-5819-8774

http://www.mitsubishicarbide.com/en/

(Tools specifications subject to change without notice.)

For Your Safety

Don't handle inserts and chips without gloves. Please machine within the recommended application range and exchange expired tools with new ones in advance of breakage. Please use safety covers and wear safety glasses. When using compounded cutting oils, please take fire precautions. When attaching inserts or spare parts, please use only the correct wrench or driver. When using rotating tools, please make a trial run to check run-out, vibration and abnormal sounds etc.



MITSUBISHI MATERIALS CORPORATION

MMC HARDMETAL INDIA PVT LTD

Head Office

Prasad Enclave, #118/119, 1st Floor, 2nd Stage BBMP Ward #11, (New #38),Industrial Suburb, Yeshwanthpura, Bengaluru-560 022 Karnataka, India, Tel: +91 80 2204 3600 E-mail: mb-mmci@mmc.co.jp

REGIONAL OFFICES:

Pune Office

Plot No, A-27 & A-28, H-Block, Pimpri Waghere, Pimpri Industrial Area MIDC, Pune – 411018, Maharashtra, India Tel :: +91 020-27456959

Gurugram Office #407, 4th Floor, JMD Galleria, Sohna Road, Opposite Malibu Town, Sector-48, Gurgaon-122 001 Haryana, India. Tel: +91 124 4089163

Chennai OfficeMM Complex,2Nd Floor,Part 30/10 Hopman 2nd Street, 100 Feet Main Road,Alandur, Chennai - 600 016 Tamilnadu, India. Tel: +91 44 4550 7006

Ahmedabad Office

210, Sigma Arcade, 2nd Floor, Visat Circle, Ahmedabad-Mehsana Road, Chandkheda, Ahmedabad – 382 424, Gujarat, India. Tel: +91 79 2329 9300

http://www.mitsubishicarbide.com/en/

(Tools specifications subject to change without notice.)